

(12)

(21) **2 518 141**

(51) Int. Cl.:

(22) **02.09.2005**

C07C 275/60 (2006.01)

C07C 275/62 (2006.01)

C08G 18/78 (2006.01)

C09D 175/04 (2006.01)

(30) **1020040435405 DE 09.09.2004**

(71)

**BAYER MATERIALSCIENCE AG,
51368, LEVERKUSEN, XX (DE).**

**MUNDSTOCK, HOLGER (DE).
GRESZTA-FRANZ, DOROTA (DE).
RICHTER, FRANK (DE).
SCHMITZ, JOERG (DE).
WEIKARD, JAN (DE).
FISCHER, WOLFGANG (DE).**

(72)

DETREMBLEUR, CHRISTOPHE (BE).

(74)

OGILVY RENAULT LLP/S.E.N.C.R.L.,S.R.L.

(54) **LIANTS DE FAIBLE VISCOSITE COMPORTANT DES GROUPES ALLOPHANATES DURCISABLES SOUS RAYONNEMENT**

(54) **LOW VISCOSITY ALLOPHANATES CONTAINING ACTINICALLY CURABLE GROUPS**

(57)

The present invention relates to a process for preparing radiation-curing binders containing allophanate groups by reacting at temperatures of .ltoreq.130.degree.C A) one or more compounds containing uretdione groups with B) one or more OH-functional compounds which contain groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation (radiation-curing groups), C) optionally NCO-reactive compounds other than B), in the presence of D) a catalyst containing at least one zinc compound, to form allophanate groups by opening the uretdione ring. The present invention also relates to the binders obtained by the process of the invention and to coating compositions containing these binders.



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2518141 A1 2006/03/09

(21) **2 518 141**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(22) Date de dépôt/Filing Date: 2005/09/02

(41) Mise à la disp. pub./Open to Public Insp.: 2006/03/09

(30) Priorité/Priority: 2004/09/09 (1020040435405) DE

(51) Cl.Int./Int.Cl. *C07C 275/62* (2006.01),
C09D 175/04 (2006.01), *C08G 18/78* (2006.01),
C07C 275/60 (2006.01)

(71) Demandeur/Applicant:
BAYER MATERIALSCIENCE AG, DE

(72) Inventeurs/Inventors:
WEIKARD, JAN, DE;
DETREMBLEUR, CHRISTOPHE, BE;
GRESZTA-FRANZ, DOROTA, DE;
RICHTER, FRANK, DE;
FISCHER, WOLFGANG, DE;
SCHMITZ, JOERG, DE;
MUNDSTOCK, HOLGER, DE

(74) Agent: OGILVY RENAULT LLP/S.E.N.C.R.L./S.R.L.

(54) Titre : LIANTS DE FAIBLE VISCOSITE COMPORTANT DES GROUPES ALLOPHANATES DURCISABLES SOUS RAYONNEMENT

(54) Title: LOW VISCOSITY ALLOPHANATES CONTAINING ACTINICALLY CURABLE GROUPS

(57) Abrégé/Abstract:

The present invention relates to a process for preparing radiation-curing binders containing allophanate groups by reacting at temperatures of $\leq 130^{\circ}\text{C}$ A) one or more compounds containing uretdione groups with B) one or more OH-functional compounds which contain groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation (radiation-curing groups), C) optionally NCO-reactive compounds other than B), in the presence of D) a catalyst containing at least one zinc compound, to form allophanate groups by opening the uretdione ring. The present invention also relates to the binders obtained by the process of the invention and to coating compositions containing these binders.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cipo.gc.ca>

OPIC • CIPO 191

OPIC



CIPO

PO8541
BMS 04 1 028-US

**LOW-VISCOSITY ALLOPHANATES CONTAINING
ACTINICALLY CURABLE GROUPS**

ABSTRACT OF THE DISCLOSURE

The present invention relates to a process for preparing radiation-curing binders containing allophanate groups by reacting at temperatures of $\leq 130^{\circ}\text{C}$

- A) one or more compounds containing uretdione groups with
 - B) one or more OH-functional compounds which contain groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation (radiation-curing groups),
 - C) optionally NCO-reactive compounds other than B),
- in the presence of
- D) a catalyst containing at least one zinc compound,
- to form allophanate groups by opening the uretdione ring.

The present invention also relates to the binders obtained by the process of the invention and to coating compositions containing these binders.

PO8541

BMS 04 1 028-US TM/li/XP

5

**LOW VISCOSITY ALLOPHANATES CONTAINING
ACTINICALLY CURABLE GROUPS**

BACKGROUND OF THE INVENTION

Field of the Invention

10 The present invention relates to low viscosity reaction products of alcohols with polyisocyanates, the alcohols containing activated groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation, to a process for preparing them and to their use in coating compositions.

15 **Description of Related Art**

The curing of coating systems which carry activated double bonds by actinic radiation, such as UV light, IR radiation or electron beams, is known and is established in industry. It is one of the most rapid curing methods in coating technology. Coating compositions based on this principle are thus referred to as
20 radiation- or actinically curing or curable systems.

Because of the environmental and economic requirements imposed on modern coating systems, i.e., that they should use as little organic solvents as possible, or none at all, for adjusting the viscosity, there is a desire to use coatings raw
25 materials which are already of low viscosity. Known for this purpose are polyisocyanates having allophanate groups as described, inter alia, in EP-A 0 682 012.

In industry these substances are prepared by reacting a monohydric or polyhydric
30 alcohol with excess aliphatic and/or cycloaliphatic diisocyanate (cf. GB-A 994 890, EP-A 0 000 194 or EP-A 0 712 840). This is followed by removal of unreacted diisocyanate by means of distillation under reduced pressure. According to DE-A 198 60 041 this procedure can also be carried out with OH-functional compounds having activated double bonds, such as hydroxyalkyl acrylates,

BMS 04 1 028-US

- 2 -

although difficulties occur in relation to the preparation of particularly low-monomer products. Since the distillation step has to take place at temperatures up to 135°C, in order to be able to lower the residue isocyanate content sufficiently (< 0.5% by weight of residual monomer), it is possible for double bonds to react, with polymerization, under thermal initiation, even during the purification process, meaning that ideal products are no longer obtained.

The preparation of low-monomer-content, allophanate-containing, polyurethane-based, radiation-curing binders is described in EP-A 0 867 457 and US-A 5 739 251. These binders, however, do not carry activated double bonds but instead carry inert allyl ether groups (structure $R-O-CH_2-CH=CH_2$). It is therefore necessary to add reactive diluents (low molecular weight esters of acrylic acid), which introduce the required UV reactivity.

EP-A 0 825 211 describes a process for synthesizing allophanate groups from oxadiazinetrienes, although no radiation-curing derivatives having activated double bonds are known. All that is mentioned is the use of maleate- and/or fumarate-containing polyesters; the possibility of radiation curing is not described. US-A 5 777 024 describes the preparation of low-viscosity radiation-curing allophanates by reacting hydroxy-functional monomers which carry activated double bonds with isocyanate groups of allophanate-modified isocyanurate polyisocyanates. The allophanate-bound radicals are saturated as a result.

The formation of allophanate compounds by ring opening of uretdiones with alcohols is known in principle as a crosslinking mechanism in powder coating materials (cf. Proceedings of the International Waterborne, High-Solids, and Powder Coatings Symposium 2001, 28th, 405-419, and also US-A 2003/0153713). Nevertheless, the reaction temperatures required for this purpose are too high ($\geq 130^\circ\text{C}$) for a targeted preparation of radiation-curing monomers based on allophanate with activated double bonds.

BMS 04 1 028-US

- 3 -

Historically the direct reaction of uretdione rings with alcohols to allophanates was first investigated for solventborne, isocyanate-free, 2K [2-component] polyurethane coating materials. Without catalysis this reaction is of no technical importance, due to the low reaction rate (F. Schmitt, *Angew. Makromol. Chem.* (1989), 171, pp. 21-38). With appropriate catalysts, however, the crosslinking reaction between HDI-based uretdione curatives and polyols is said to begin at 60 to 80°C (K. B. Chandalia; R. A Englebach; S. L. Goldstein; R. W. Good; S. H. Harris; M. J. Morgan; P. J. Whitman; R. T. Wojcik, *Proceedings of the International Waterborne, High-Solids, and Powder Coatings Symposium*, (2001), pp. 77-89). The structure of these catalysts has not been published to date. Commercial products prepared by utilizing this reaction are also undisclosed to date.

In summary it may be stated that the preparation of low-viscosity radiation-curing allophanates by ring-opening reaction of alcohols carrying activated double bonds with uretdiones at temperatures $\leq 130^{\circ}\text{C}$ is not disclosed in detail in the prior art.

Surprisingly it has now been found that from the reaction of uretdiones with olefinically unsaturated alcohols, preferably containing activated double bonds, low-viscosity radiation-curing allophanates, which have a low residual monomer content and preferably have viscosities measured at 23°C of less than 100 000 mPas, can be obtained using specific zinc compounds as catalysts even at temperatures under 130°C .

SUMMARY OF THE INVENTION

The present invention relates to a process for preparing radiation-curing binders containing allophanate groups reacting at temperatures of $\leq 130^{\circ}\text{C}$

A) one or more compounds containing uretdione groups with

BMS 04 1 028-US

- 4 -

- B) one or more OH-functional compounds which contain groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation (radiation-curing groups),
- C) optionally NCO-reactive compounds other than B),
- 5 in the presence of
- D) a catalyst containing at least one zinc compound, to form allophanate groups by opening the uretdione ring.

The present invention also relates to the binders obtained by the process of the

10 invention.

- The present invention further relates to coating compositions containing
- a) one or more of the binders obtained in accordance with the invention,
- b) optionally one or more polyisocyanates containing free or blocked
- 15 isocyanate groups, which are free from groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation,
- c) optionally compounds other than a), which contain groups which react, with polymerization, with ethylenically unsaturated compounds on
- 20 exposure to actinic radiation, and optionally contain free or blocked NCO groups,
- d) optionally one or more isocyanate-reactive compounds containing active hydrogen,
- e) one or more initiators, and
- 25 f) optionally solvents.

DETAILED DESCRIPTION OF THE INVENTION

Suitable compounds for use as component A) include all organic compounds which contain at least one uretdione group. Preferably they are compounds

30 obtained by the catalytic dimerization of aliphatic, cycloaliphatic and/or

BMS 04 1 028-US

- 5 -

araliphatic diisocyanates or polyisocyanates by known methods (cf. J. Prakt. Chem. 1994, 336, page 196-198).

Examples of suitable diisocyanates include 1,4-diisocyanatobutane, 1,6-
 5 diisocyanatohexane (HDI), trimethylhexane diisocyanate, 1,3- and 1,4-bis-
 isocyanatomethylcyclohexane, isophorone diisocyanate (IPDI), 4,4'-
 diisocyanatodicyclohexylmethanes, 1,3- and 1,4-xylylene diisocyanates (XDI
 commercial product from Takeda, Japan), diphenylmethane 4,4'-diisocyanate and
 diphenylmethane 2,4'-diisocyanate (MDI), 2,4- and 2,6-toluene diisocyanate
 10 (TDI), or mixtures thereof. 1,6-Diisocyanatohexane is preferred.

Examples of catalysts employed for the dimerization reaction include
 trialkylphosphines, dimethylaminopyridines and tris(dimethylamino)phosphine.
 The result of the dimerization reaction depends in known manner on the catalyst
 15 used, on the process conditions and on the diisocyanates employed. In particular it
 is possible for products to be formed which contain on average more than one
 uretdione group per molecule, the number of uretdione groups being subject to a
 distribution. Depending upon the catalyst used, the process conditions and the
 diisocyanates employed, product mixtures are also formed which in addition to
 20 uretdiones also contain other structural units, such as isocyanurate and/or
 iminooxadiazinedione.

Particularly preferred products may be obtained by the catalytic dimerization of
 HDI and have a free HDI content of less than 0.5% by weight; an NCO content of
 25 17 to 25% by weight, preferably of 21 to 24% by weight; and a viscosity at 23°C
 of from 20 to 500 mPas, preferably from 50 to 200 mPas.

The generally NCO-functional compounds obtained by catalytic dimerization are
 preferably used directly as part of component A), but they can also first be
 30 subjected to further reaction and then used as component A). Further reactions

BMS 04 1 028-US

- 6 -

include blocking the free NCO groups or further reaction of the NCO groups with NCO-reactive compounds having a functionality of two or more to form iminooxadiazinedione, isocyanurate, urethane, allophanate, biuret urea, oxadiazinetriene, oxazolidinone, acylurea or carbodiimide groups. This results in
5 compounds containing uretdione groups having a higher molecular weight, which, depending on the chosen proportions, may contain NCO groups or may be free from NCO groups.

Suitable blocking agents include alcohols, lactams, oximes, malonates, alkyl
10 acetoacetates, triazoles, phenols, imidazoles, pyrazoles and amines, such as butanone oxime, diisopropylamine, 1,2,4-triazole, dimethyl-1,2,4-triazole, imidazole, diethyl malonate, ethyl acetoacetate, acetone oxime, 3,5-dimethylpyrazole, ϵ -caprolactam, N-tert-butylbenzylamine, cyclopentanone carboxyethyl ester or mixtures of these blocking agents. The procedure for the
15 blocking of NCO groups is well known and described in Progress in Organic Coatings 1999, 36, 148-172.

NCO-reactive compounds having a functionality of two or more for derivatizing the uretdiones used in A) can be the preceding di- and/or polyisocyanates, and also
20 simple alcohols with a functionality of two or more, such as ethylene glycol, propane-1,2-diol, propane-1,3-diol, diethylene glycol, dipropylene glycol, the isomeric butanediols, neopentyl glycol, hexane-1,6-diol, 2-ethylhexanediol, tripropylene glycol and the alkoxylated derivatives of these alcohols. Preferred dihydric alcohols are hexane-1,6-diol, dipropylene glycol and tripropylene glycol.
25 Suitable trihydric alcohols include glycerol or trimethylolpropane or their alkoxylated derivatives. Tetrahydric alcohols include pentaerythritol or its alkoxylated derivatives.

BMS 04 1 028-US

- 7 -

By actinic radiation is meant electromagnetic, ionizing radiation, especially electron beams, UV radiation and also visible light (Roche Lexikon Medizin, 4th edition; Urban & Fischer Verlag, Munich 1999).

- 5 Component B is selected from compounds having groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation (radiation-curing groups). Examples include vinyl, vinyl ether, propenyl, allyl, maleyl, fumaryl, maleimide, dicyclopentadienyl, acrylamide, acrylic and methacrylic groups, preferably vinyl ether, acrylate and/or methacrylate groups,
10 and more preferably acrylate groups.

- Examples of suitable hydroxyl-containing compounds B) include 2-hydroxyethyl (meth)acrylate, polyethylene oxide mono(meth)acrylate (e.g. PEA6/PEM6; Laporte Performance Chemicals Ltd., UK), polypropylene oxide
15 mono(meth)acrylate (e.g. PPA6, PPM5S; Laporte Performance Chemicals Ltd., UK), polyalkylene oxide mono(meth)acrylate (e.g. PEM63P, Laporte Performance Chemicals Ltd., UK), poly(ϵ -caprolactone) mono(meth)acrylates (e.g. Tone M100[®] Dow, Schwalbach, DE), 2-hydroxypropyl (meth)acrylate, 4-hydroxybutyl (meth)acrylate, hydroxybutyl vinyl ether, 3-hydroxy-2,2-dimethylpropyl
20 (meth)acrylate, the hydroxy-functional mono-, di- or higher functional acrylates such as glyceryl di(meth)acrylate, trimethylolpropane di(meth)acrylate, pentaerythritol tri(meth)acrylate or dipentaerythritol penta(meth)acrylate, which are obtained by reacting polyhydric, optionally alkoxylated, alcohols such as trimethylolpropane, glycerol, pentaerythritol or dipentaerythritol with
25 (meth)acrylic acid.

Also suitable as component B) are alcohols obtained from the reaction of acids containing double bonds with epoxide compounds optionally containing double bonds, such as the reaction products of (meth)acrylic acid with glycidyl

BMS 04 1 028-US

- 8 -

(meth)acrylate or bisphenol A diglycidyl ether. Additionally, it is also possible to use unsaturated alcohols which are obtained from the reaction of optionally unsaturated acid anhydrides with hydroxy compounds and epoxide compounds that optionally contain acrylate groups. Examples include the reaction products of maleic anhydride with 2-hydroxyethyl (meth)acrylate and glycidyl (meth)acrylate. Preferably, the compounds of component B) correspond to the preceding compounds that have an OH functionality of from 0.9 to 1.1. More preferably, compounds containing primary hydroxyl groups are used in B), such as 2-hydroxyethyl acrylate and 4-hydroxybutyl acrylate.

10

Besides the OH-functional unsaturated compounds of component B) it is possible in the process of the invention to also use compounds C), which are different from those of B) and contain NCO-reactive groups such as OH, SH or NH. Examples include NH- or SH-functional compounds containing groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation.

15

Additionally it is possible to incorporate groups having a hydrophilic action, particularly if use from an aqueous medium is envisaged, such as in an aqueous coating material. Groups with a hydrophilic action include ionic groups, which may be either cationic or anionic in nature, and/or nonionic hydrophilic groups. Cationically, anionically or nonionically dispersing compounds are those which contain, for example, sulphonium, ammonium, phosphonium, carboxylate, sulphonate or phosphonate groups or the groups which can be converted into these groups by forming salts (potential ionic groups) or which contain polyether groups and can be incorporated by means of existing isocyanate-reactive groups. Preferred isocyanate-reactive groups are hydroxyl and amino groups.

20

25

Examples of suitable ionic compounds or compounds containing potential ionic groups are mono- and dihydroxycarboxylic acids, mono- and diaminocarboxylic


30

BMS 04 1 028-US

- 9 -

- acids, mono- and dihydroxysulphonic acids, mono- and diaminosulphonic acids, mono- and dihydroxyphosphonic acids or mono- and diaminophosphonic acids and their salts. Examples include dimethylol propionic acid, dimethyl-olbutyric acid, hydroxypivalic acid, N-(2-aminoethyl)- β -alanine, 2-(2-aminoethylamino)-ethanesulphonic acid, ethylenediamine-propyl- or butylsulphonic acid, 1,2- or 1,3-propylenediamine- β -ethylsulphonic acid, malic acid, citric acid, glycolic acid, lactic acid, glycine, alanine, taurine, lysine, 3,5-diaminobenzoic acid, an adduct of IPDI and acrylic acid (EP-A 0 916 647, Example 1) and its alkali metal and/or ammonium salts, the adduct of sodium bisulphite with but-2-ene-1,4-diol, polyethersulphonate, the propoxylated adduct of 2-butenediol and NaHSO_3 (described for example in DE-A 2 446 440, page 5-9, formula I-III) and also structural units which can be converted into cationic groups, such as N-methyldiethanolamine.
- Preferred ionic or potential ionic compounds are those having carboxyl or carboxylate, sulphonate groups and/or ammonium groups. Particularly preferred ionic compounds are those which contain carboxyl and/or sulphonate groups as ionic or potential ionic groups, such as the salts of N-(2-aminoethyl)- β -alanine, 2-(2-aminoethylamino)ethanesulphonic acid, the adduct of IPDI and acrylic acid (EP-A-0 916 647, Example 1) and also dimethylolpropionic acid.

- Suitable nonionic hydrophilic compounds include polyoxyalkylene ethers containing at least one hydroxyl or amino group. These polyethers include a fraction of from 30% to 100% by weight of units derived from ethylene oxide.
- Suitable compounds include linear polyethers having a functionality of from 1 to 3, and also compounds of formula (I),



BMS 04 1 028-US

- 10 -

wherein

R^1 and R^2 independently of one another are each a divalent aliphatic, cycloaliphatic or aromatic radical having 1 to 18 carbon atoms, which may be interrupted by oxygen and/or nitrogen atoms, and

5 R^3 is an alkoxy-terminated polyethylene oxide radical.

Nonionic hydrophilic compounds also include monohydric polyalkylene oxide polyether alcohols containing on average 5 to 70, preferably 7 to 55, ethylene oxide units per molecule, such as those obtained in known manner by alkoxyating suitable starter molecules (e.g. in Ullmanns Encyclopädie der technischen Chemie,
10 4th edition, volume 19, Verlag Chemie, Weinheim pp. 31-38).

Examples of suitable starter molecules include saturated monoalcohols such as methanol, ethanol, n-propanol, isopropanol, n-butanol, isobutanol, sec-butanol, the isomeric pentanols, hexanols, octanols and nonanols, n-decanol, n-dodecanol, n-
15 tetradecanol, n-hexadecanol, n-octadecanol, cyclohexanol, the isomeric methylcyclohexanols, hydroxymethylcyclohexane, 3-ethyl-3-hydroxymethyloxetane, tetrahydrofurfuryl alcohol, diethylene glycol monoalkyl ethers such as diethylene glycol monobutyl ether, unsaturated alcohols (such as allyl alcohol, 1,1-dimethylallyl alcohol or oleyl alcohol), aromatic alcohols such as
20 phenol, the isomeric cresols or methoxyphenols, araliphatic alcohols (such as benzyl alcohol, anisyl alcohol or cinnamyl alcohol), secondary monoamines (such as dimethylamine, diethylamine, dipropylamine, diisopropylamine, dibutylamine, bis(2-ethylhexyl)amine, N-methyl- and N-ethylcyclohexylamine or dicyclohexylamine) and also heterocyclic secondary amines (such as morpholine,
25 pyrrolidine, piperidine or 1H-pyrazole). Preferred starter molecules are saturated monoalcohols. Particular preference is given to using diethylene glycol monobutyl ether as the starter molecule.

BMS 04 1 028-US

- 11 -

Alkylene oxides suitable for the alkoxylation reaction include, in particular, ethylene oxide and propylene oxide, which can be used in any order or in a mixture in the alkoxylation reaction.

- 5 The polyalkylene oxide polyether alcohols are either straight polyethylene oxide polyethers or mixed polyalkylene oxide polyethers wherein at least 30 mole %, preferably at least 40 mole %, of the alkylene oxide units are ethylene oxide units. Preferred nonionic compounds are monofunctional mixed polyalkylene oxide polyethers which contain at least 40 mole % of ethylene oxide units and not more
10 than 60 mole % of propylene oxide units.

Especially when using a hydrophilic agent containing ionic groups it is necessary to investigate its effect on the action of catalyst D). For this reason preference is given to nonionic compounds as hydrophilic agents.

15

Suitable catalyst compounds D) include, in addition to the zinc compounds for use in accordance with the invention, the compounds known for catalyzing the reaction of isocyanate groups with isocyanate-reactive groups, individually or in mixtures with one another.

20

- Examples include tertiary amines such as triethylamine, pyridine, methylpyridine, benzyldimethylamine, N,N-endoethylenepiperazine, N-methylpiperidine, penta-methyldiethylenetriamine, N,N-dimethylaminocyclohexane, N,N'-dimethylpiperazine or 1,4-diazabicyclo[2.2.2]octane (DABCO), or metal salts
25 such as iron(III) chloride, tin(II) octoate, tin(II) ethylcaproate, tin(II) palmitate, dibutyltin(IV) dilaurate, dibutyltin(IV) diacetate and molybdenum glycolate or mixtures of such catalysts.

- Suitable zinc compounds include any organic or inorganic zinc compounds, such
30 as zinc oxide, zinc sulphide, zinc carbonate, zinc fluoride, zinc chloride, zinc

BMS 04 1 028-US

- 12 -

bromide, zinc iodide, zinc phosphate, zinc borate, zinc titanate, zinc hexafluorosilicate, zinc sulphite, zinc sulphate, zinc nitrate, zinc tetrafluoroborate, zinc acetate, zinc octoate, zinc cyclohexanecarboxylate, zinc laurate, zinc palmitate, zinc stearate, zinc behenate, zinc citrate, zinc gluconate, zinc acetylacetonate, zinc 2,2,6,6-tetramethyl-3,5-heptanedionate, zinc trifluoroacetate, zinc trifluoromethanesulphonate, zinc dimethyldithiocarbamate and mixtures of these compounds.

Preferred catalysts D) are zinc octoate and/or zinc acetylacetonate. Preferably, zinc compounds are exclusively used as catalysts D).

- 10 It is also possible to apply catalysts D) to support materials by known methods and to use them as heterogeneous catalysts.

The compounds of catalyst component D) can be dissolved advantageously in one of the components used in the process, or in a portion thereof. In particular, the zinc compounds for use in accordance with the invention dissolve very well in the polar hydroxyalkyl acrylates, so that D) in solution in small amounts of B) can be metered in as a concentrated solution in liquid form.

In the process of the invention catalyst component D) is preferably used in amounts of 0.001 to 5.0% by weight, more preferably 0.01 to 2.0% by weight and most preferably 0.05 to 1.0% by weight, based on solids content of the product.

As component E) it is possible to use solvents or reactive diluents. Suitable solvents are inert towards the functional groups present in the product from the time of their addition until the end of the process. Suitable solvents include those used in the coating industry, such as hydrocarbons, ketones and esters, e.g. toluene, xylene, isooctane, acetone, butanone, methyl isobutyl ketone, ethyl acetate, butyl acetate, tetrahydrofuran, N-methylpyrrolidone, dimethylacetamide and dimethylformamide. It is preferred not to add any solvent.

BMS 04 1 028-US

- 13 -

As reactive diluents it is possible to use compounds which during UV curing are also (co)polymerized and hence incorporated into the polymer network and inert towards NCO groups. Such reactive diluents are described, by way of example, in P. K. T. Oldring (Ed.), Chemistry & Technology of UV & EB Formulations For Coatings, Inks & Paints, Vol. 2, 1991, SITA Technology, London, pp. 237-285. They may be esters of acrylic acid or methacrylic acid, preferably acrylic acid, with mono- or polyfunctional alcohols. Examples of suitable alcohols include the isomeric butanols, pentanols, hexanols, heptanols, octanols, nonanols and decanols; cycloaliphatic alcohols such as isobornol, cyclohexanol and alkylated cyclohexanols; dicyclopentanol; arylaliphatic alcohols such as phenoxyethanol and nonylphenylethanol; and tetrahydrofurfuryl alcohols. Additionally, it is possible to use alkoxyated derivatives of these alcohols.

Suitable dihydric alcohols include alcohols such as ethylene glycol, propane-1,2-diol, propane-1,3-diol, diethylene glycol, dipropylene glycol, the isomeric butanediols, neopentyl glycol, hexane-1,6-diol, 2-ethylhexanediol, tripropylene glycol or alkoxyated derivatives of these alcohols. Preferred dihydric alcohols are hexane-1,6-diol, dipropylene glycol and tripropylene glycol. Suitable trihydric alcohols include glycerol or trimethylolpropane or their alkoxyated derivatives. Tetrahydric alcohols include pentaerythritol or its alkoxyated derivatives.

The binders of the invention must be stabilized against premature polymerization. Therefore, as a constituent of component E), before and/or during the reaction, preferably phenolic stabilizers are added which inhibit the polymerization. Use is made in this context of phenols such as para-methoxyphenyl, 2,5-di-tert-butylhydroquinone or 2,6-di-tert-butyl-4-methylphenol. Also suitable are N-oxyl compounds for stabilization, such as 2,2,6,6-tetramethylpiperidine N-oxide (TEMPO) or its derivatives. The stabilizers can also be incorporated chemically into the binder; suitability in this context is possessed by compounds of the abovementioned classes, especially if they still carry further free aliphatic alcohol

BMS 04 1 028-US

- 14 -

groups or primary or secondary amine groups and thus can be attached chemically to compounds of component A) by way of urethane or urea groups. Particularly suitable for this purpose are 2,2,6,6-tetramethyl-4-hydroxypiperidine N-oxide. Preferred are phenolic stabilizers, especially para-methoxyphenol and/or 2,6-di-
5 tert-butyl-4-methylphenol.

Other stabilizers, such as hindered amine light stabilizers (HALS), in contrast, are used less preferably in E), since they are known not to enable such effective stabilization and instead may lead to "creeping" free-radical polymerization of
10 unsaturated groups.

In order to stabilize the reaction mixture, in particular the unsaturated groups, against premature polymerization it is possible to pass an oxygen-containing gas, preferably air, into and/or over the reaction mixture. It is preferred for the gas to
15 have a very low moisture content in order to prevent unwanted reaction in the presence of isocyanate.

In general a stabilizer is added during the preparation of the binders of the invention, and at the end, in order to achieve a long-term stability, stabilization is
20 repeated with a phenolic stabilizer, and optionally the reaction product is saturated with air.

In the process of the invention the stabilizer component is typically used in amounts of 0.001 to 5.0% by weight, preferably 0.01 to 2.0% by weight and more
25 preferably 0.05 to 1.0% by weight, based on the solids content of the product.

The ratio of OH groups from component B) to the sum of NCO and uretdione groups from A) is preferably from 1.5:1.0 to 1.0:1.9, more preferably from 1.0:1.0 to 1.0:1.9 and most preferably from 1.0:1.0 to 1.0:1.2. The process of the

BMS 04 1 028-US

- 15 -

invention is preferably carried out at temperatures of 20 to 130°C, more preferably of 40 to 100°C and most preferably of 80 to 90°C.

Normally the NCO groups that may be present react more rapidly with the hydroxyl groups of component B) than do the uretdione groups of component A). Therefore, if two or more different constituents are present in B), it is possible to control the urethanization and allophanatization by means of the sequence of addition of the constituents such that one constituent of B) is preferably incorporated during the urethanization reaction, while the constituent added last is preferably incorporated during the allophanatization reaction.

The reaction of component A) with B) and further NCO-reactive compounds C) is over when all of the NCO groups, in accordance with the chosen stoichiometric proportions, have reacted with NCO-reactive groups from B) and C) and all uretdione groups, in accordance with the chosen stoichiometric proportions, have reacted with the hydroxyl groups from B). It is also possible to end the allophanatization by adding catalyst-deactivating compounds (for example, strong acids such as acidic phosphoric esters) or adding other isocyanate-containing compounds which scavenge the remaining compounds of component B).

20

It is immaterial whether the process of the invention is carried out continuously, for example, in a static mixer, extruder or compounder or batchwise, for example, in a stirred reactor. Preferably, the process of the invention is carried out in a stirred reactor, the sequence of addition of components A)-E) being arbitrary.

25

The course of the reaction can be monitored by means of suitable measuring instruments installed in the reaction vessel and/or on the basis of analyses on samples taken. Suitable techniques are known. They include viscosity measurements, measurements of the refractive index or the OH content, gas chromatography (GC), nuclear magnetic resonance spectroscopy (NMR), infrared

30

BMS 04 1 028-US

- 16 -

spectroscopy (IR) and near infrared spectroscopy (NIR). Preference is given to using IR to check for any free NCO groups present (for aliphatic NCO groups, band at approximately $\nu = 2272 \text{ cm}^{-1}$) and, in particular, for uretdione groups (e.g. band for uretdiones based on hexamethylene diisocyanate at $\nu = 1761 \text{ cm}^{-1}$) and to

5 GC analyses for unreacted compounds from B) and C).

In one preferred embodiment of the invention there is parallel allophanatization and urethanization of the compounds of component A). For that purpose A) is introduced initially, then stabilizers and, where appropriate, additives from E) are

10 added, subsequently components B)-E) are added and the reaction mixture is brought to reaction temperature.

In another preferred embodiment initially A) is reacted with B) until the NCO groups have reacted completely. E) or parts thereof may already be present.

15 Subsequently the reaction of the uretdione groups of A) with B) is initiated by adding D) and additionally, where appropriate, by adapting the temperature.

In one particularly preferred embodiment the isocyanate groups and the uretdione groups are reacted with an excess of hydroxyl groups of component B. The

20 hydroxyl groups which remain following the reaction of A) with B), with catalysis of D), are subsequently reacted preferably with further isocyanate-containing compounds, in particular with those compounds described as component B), with urethanization.

25 The unsaturated allophanates obtained by the process of the invention preferably have viscosities measured using a cone-plate viscosimeter at 23°C of $\leq 100\,000 \text{ mPas}$, more preferably $\leq 75\,000 \text{ mPas}$; preferably have number average molecular weights M_n of from 600 to 3000 g/mol , more preferably from 750 to

BMS 04 1 028-US

- 17 -

1500 g/mol; and preferably contain less than 0.5% by weight of free di- and/or triisocyanate monomers, more preferably less than 0.1% by weight.

The binders of the invention can be used for producing coatings and paints and
5 also adhesives, printing inks, casting resins, dental compounds, sizes, photoresists, stereolithography systems, resins for composite materials and sealants. In the case of adhesive bonding or sealing, it is a requirement, in the case of UV radiation curing, at least one of the two substrates to be bonded or sealed to one another is permeable to UV radiation, i.e, it must be transparent. In the case of electron
10 beams, sufficient permeability for electrons should be ensured. Preferably, the binders are used in paints and coatings.

The coating compositions according to the invention contain

- a) one or more of the binders obtained in accordance with the invention,
- 15 b) optionally one or more polyisocyanates containing free or blocked isocyanate groups, which are free from groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation,
- c) optionally compounds other than a), which contain groups which react,
20 with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation, and optionally contain free or blocked NCO groups,
- d) optionally one or more isocyanate-reactive compounds,
- e) initiators, and
- 25 f) optionally solvents.

The polyisocyanates of component b), which are used in the coating compositions according to the invention, are known. Preferred are polyisocyanates which optionally contain isocyanurate, allophanate, biuret, uretdione and/or
30 iminooxadiazinedione groups and are prepared from hexamethylene diisocyanate,

BMS 04 1 028-US

- 18 -

isophorone diisocyanate, 4,4'-diisocyanatodicyclohexylmethane and/or trimethylhexamethylene diisocyanate. The NCO groups may also be blocked with the blocking agents previously described as suitable for blocking component A).

- 5 Compounds c) include urethane acrylates prepared from hexamethylene diisocyanate, isophorone diisocyanate, 4,4'-diisocyanatodicyclohexylmethane and/or trimethylhexamethylene diisocyanate, which may have been modified to contain isocyanurate, allophanate, biuret, uretdione and/or iminooxadiazinedione groups, and which do not contain isocyanate-reactive groups. NCO-containing
- 10 urethane acrylates are available commercially from Bayer MaterialScience AG, Leverkusen, DE as Roskydal® UA VP LS 2337, Roskydal® UA VP LS 2396 or Roskydal® UA XP 2510.

- Also suitable as component c) are the reactive diluents already described and
- 15 known in the art of radiation-curing coatings, provided that they do not contain any NCO-reactive groups.

- Compounds d) can be saturated or unsaturated and contain isocyanate-reactive groups, such as hydroxyl, amine or thiol. Preferred are saturated polyhydroxy
- 20 compounds, such as polyether polyols, polyester polyols, polycarbonate polyols, poly(meth)acrylate polyols and/or polyurethane polyols which are known from the technology of coating, adhesive bonding, printing inks or sealants and which contain no groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation.

25

Unsaturated hydroxy-functional compounds include the epoxy acrylates, polyester acrylates, polyether acrylates, urethane acrylates and acrylated polyacrylates which are known in the art of radiation-curing coatings and have an OH number of from 30 to 300 mg KOH/g. It is also possible to use the reactive diluents, previously

BMS 04 1 028-US

- 19 -

described and known in the art of radiation-curing coatings, as a constituent of d), provided that they contain NCO-reactive groups.

Suitable initiators for free-radical polymerization, which can be used as
5 component e), are those which can be activated thermally and/or by radiation. Photoinitiators, which are activated by UV or visible light, are preferred in this context. The photoinitiators are known compounds. A distinction is made between unimolecular (type I) and bimolecular (type II) initiators. Suitable (type I) systems include aromatic ketone compounds, e.g. benzophenones in combination with
10 tertiary amines, alkylbenzophenones, 4,4'-bis(dimethylamino)benzophenone (Michler's ketone), anthrone and halogenated benzophenones or mixtures thereof. Suitable (type II) initiators include benzoin and its derivatives, benzil ketals, acylphosphine oxides, 2,4,6-trimethylbenzoyldiphenylphosphine oxide, bisacylphosphine oxides, phenylglyoxylic esters, camphorquinone, α -
15 aminoalkylphenones, α,α -dialkoxyacetophenones and α -hydroxyalkylphenones.

The initiators are used in amounts of 0.1% to 10% by weight, preferably 0.1% to 5% by weight, based on the weight of the film-forming binder. The initiators can be used individually or, to obtain advantageous synergistic effects, in combination
20 with one another.

When electron beams are used instead of UV irradiation there is no need for a photoinitiator. Electron beams are generated by means of thermal emission and accelerated by way of a potential difference. The high-energy electrons then pass
25 through a titanium foil and are guided onto the binders to be cured. The general principles of electron beam curing are described in detail in "Chemistry & Technology of UV & EB Formulations for Coatings, Inks & Paints", Vol. 1, P.K.T Oldring (Ed.), SITA Technology, London, England, pp. 101-157, 1991.

BMS 04 1 028-US

- 20 -

Thermal curing of the activated double bonds can take place with the addition of thermally decomposing free-radical initiators. Suitable initiators include peroxy compounds such as dialkoxy dicarbonates, for example, bis(4-tert-butylcyclohexyl) peroxydicarbonate; dialkyl peroxides such as dilauryl peroxide; 5 peresters of aromatic or aliphatic acids such as tert-butyl perbenzoate or tert-amyl peroxy 2-ethylhexanoate; inorganic peroxides such as ammonium peroxodisulphate or potassium peroxodisulphate; organic peroxides such as 2,2-bis(tert-butylperoxy)butane, dicumyl peroxide or tert-butyl hydroperoxide; and azo compounds such as 2,2'-azobis[N-(2-propenyl)-2-methylpropionamides], 1- 10 [(cyano-1-methylethyl)azo]formamides, 2,2'-azobis(N-butyl-2-methylpropionamides), 2,2'-azobis(N-cyclohexyl-2-methylpropionamides), 2,2'-azobis{2-methyl-N-[2-(1-hydroxybutyl)]propionamides}, 2,2'-azobis{2-methyl-N-[2-(1-hydroxybutyl)]propionamides, or 2,2'-azobis{2-methyl-N-[1,1-bis(hydroxymethyl)-2-hydroxyethyl] propionamides. Also suitable are highly substituted 1,2- 15 diphenylethanes (benzpinacols) such as 3,4-dimethyl-3,4-diphenylhexane, 1,1,2,2-tetraphenylethane-1,2-diol or the silylated derivatives thereof.

It is also possible to use a combination of initiators activable by UV light and thermally.

20

Additives e) include solvents of the type specified above under E). Additionally, it is possible for e), in order to increase the weather stability of the cured coating film, to contain UV absorbers and/or HALS stabilizers. Preferred is a combination of these stabilizers. The UV absorbers should have an absorption range of not 25 more than 390 nm, such as the triphenyltriazine types (e.g. Tinuvin[®] 400 (Ciba Spezialitätenchemie GmbH, Lampertheim, DE)), benzotriazoles such as Tinuvin[®] 622 (Ciba Spezialitätenchemie GmbH, Lampertheim, DE) or oxalic dianilides (e.g. Sanduvor[®] 3206 (Clariant, Muttens, CH)). They are added at 0.5% to 3.5% by weight, based on resin solids. Suitable HALS stabilizers are also available 30 commercially and include (Tinuvin[®] 292 or Tinuvin[®] 123 (Ciba

BMS 04 1 028-US

- 21 -

Spezialitätenchemie GmbH, Lampertheim, DE) or Sanduvor[®] 3258 (Clariant, Muttenz, CH). They are preferably added in amounts of 0.5% to 2.5% by weight based on resin solids.

- 5 It is also possible for component e) to contain pigments, dyes, fillers, levelling additives and devolatilizing additives.

Additionally it is possible, if necessary, for the catalysts known from polyurethane chemistry for accelerating the NCO/OH reaction to be present in e). They include
 10 tin salts, zinc salts, organotin compounds, tin soaps and/or zinc soaps such as tin octoate, dibutyltin dilaurate, dibutyltin oxide or tertiary amines such as diazabicyclo[2.2.2]octane (DABCO).

The application of the coating compositions of the invention to the material to be
 15 coated takes place using the methods known in coatings technology, such as spraying, knife coating, rolling, pouring, dipping, spin coating, brushing or squirting or by means of printing techniques such as screen, gravure, flexographic or offset printing and also by means of transfer methods.

- 20 Suitable substrates include wood, metal, including in particular metal as used in the applications of wire enamelling, coil coating, can coating or container coating, and also plastic, including plastic in the form of films, especially ABS, AMMA, ASA, CA, CAB, EP, UF, CF, MF, MPF, PF, PAN, PA, PE, HDPE, LDPE, LLDPE, UHMWPE, PET, PMMA, PP, PS, SB, PUR, PVC, RF, SAN, PBT, PPE,
 25 POM, PUR-RIM, SMC, BMC, PP-EPDM, and UP (abbreviations according to DIN 7728T1), paper, leather, textiles, felt, glass, wood, wood materials, cork, inorganically bonded substrates such as wooden boards and fiber cement slabs, electronic assemblies or mineral substrates. It is also possible to coat substrates containing a variety of the preceding materials, or to coat already coated substrates
 30 such as vehicles, aircraft or boats and also parts thereof, especially vehicle bodies

BMS 04 1 028-US

- 22 -

or parts for exterior mounting. It is also possible to apply the coating compositions to a substrate temporarily, then to cure them partly or fully and optionally to detach them again, in order to produce films.

- 5 For curing it is possible to remove solvents present entirely or partly by flashing off. Subsequently or simultaneously it is possible for the optional thermal and the photochemical curing operation or operations to be carried out in succession or simultaneously.
- 10 If necessary the thermal curing can take place at room temperature or at elevated temperature, preferably at 40 to 160°C, preferably at 60 to 130°C and more preferably at 80 to 110°C.

Where photoinitiators are used in d) the radiation cure takes place preferably by
15 exposure to high-energy radiation, in other words UV radiation or daylight, such as light having a wavelength 200 to 700 nm or by bombardment with high-energy electrons (electron beams, 150 to 300 keV). Radiation sources of light or UV light include high-pressure or medium-pressure mercury vapor lamps. It is possible for the mercury vapor to have been modified by doping with other elements such as
20 gallium or iron. Lasers, pulsed lamps (known under the designation of UV flashlight lamps), halogen lamps or excimer emitters may also be used. As an inherent part of their design or through the use of special filters and/or reflectors, the emitters may be equipped so that part of the UV spectrum is prevented from being emitted. By way of example, for reasons of occupational hygiene, for
25 example, the radiation assigned to UV-C or to UV-C and UV-B may be filtered out. The emitters may be installed in stationary fashion, so that the material for irradiation is conveyed past the radiation source by means of a mechanical device, or the emitters may be mobile and the material for irradiation may remain stationary during curing. The radiation dose which is normally sufficient for
30 crosslinking in the case of UV curing is from 80 to 5000 mJ/cm².

BMS 04 1 028-US

- 23 -

Irradiation can also be carried out in the absence of oxygen, such as under an inert gas atmosphere or an oxygen-reduced atmosphere. Suitable inert gases are preferably nitrogen, carbon dioxide, noble gases or combustion gases. Irradiation
5 may additionally take place by covering the coating with media transparent to the radiation. Examples include polymeric films, glass or liquids such as water.

Depending on the radiation dose and curing conditions it is possible to vary the type and concentration of any initiator used in known manner.

10

Particular preference is given to carrying out curing using high-pressure mercury lamps in stationary installations. Photoinitiators are then employed at concentrations of from 0.1% to 10% by weight, more preferably from 0.2% to 3.0% by weight, based on the solids content of the coating composition. For
15 curing these coatings it is preferred to use a dose of from 200 to 3000 mJ/cm², measured in the wavelength range from 200 to 600 nm.

When thermally activable initiators are used in d), curing is carried out by increasing the temperature. The thermal energy may be introduced into the coating
20 by means of radiation, thermal conduction and/or convection using ovens, near-infrared lamps and/or infrared lamps that are known in coatings technology.

The applied film thicknesses (prior to curing) are typically between 0.5 and 5000 µm, preferably between 5 and 1000 µm and more preferably between 15 and
25 200 µm. Where solvents are used, they are removed after application and before curing by known methods.

BMS 04 1 028-US

- 24 -

EXAMPLES

All percentages are by weight unless indicated otherwise.

- 5 The determination of the NCO contents in % was determined by back-titration with 0.1 mol/l hydrochloric acid following reaction with butylamine in accordance with DIN EN ISO 11909.

- 10 The viscosity measurements were carried out with a cone-plate viscosimeter (SM-KP), Viskolab LC3/ISO from Paar Physica, Ostfildern, DE in accordance with ISO/DIS 3219:1990.

- 15 Infrared spectroscopy was on liquid films applied between sodium chloride plates on a model 157 instrument from Perkin Elmer, Überlingen, DE.

- 20 The amount of residue monomers and amount of volatile synthesis components were analyzed by means of GC (method using tetradecane as internal standard, oven temperature 110°C, injector temperature 150°C, carrier gas helium, instrument: 6890 N, Agilent, Waldbronn, DE, column: Restek RT 50, 30 m, 0.32 mm internal diameter, film thickness 0.25 µm).

- The solids content was determined in accordance with DIN 53216/1 draft 4/89, ISO 3251.

- 25 An ambient temperature of 23°C, which prevailed at the time when the experiments were conducted is referred to as RT.

- 30 Desmodur® N 3400 - HDI polyisocyanate predominantly containing uretdione groups, viscosity 185 mPas/23°C, NCO content 21.4%, commercial product of Bayer MaterialScience AG, Leverkusen, DE

BMS 04 1 028-US

- 25 -

Desmorapid® Z - dibutyltin dilaurate (DBTL), commercial product of Bayer
MaterialScience AG, Leverkusen, DE

- 5 Darocur® 1173 - photoinitiator, commercial product of Ciba
Spezialitätenchemie GmbH, Lampertheim, DE

Example 1 – Inventive allophanate-containing binder

- 10 A three-necked flask with reflux condenser, stirrer and dropping funnel, and
through which air was passed (0.5 l/h), was charged at RT with 263.13 g of
Desmodur® N3400, 0.50 g of 2,6-di-tert-butyl-4-methylphenol and 0.07 g of
Desmorapid® Z and this initial charge was then heated to 60°C. 219.25 g of 2-
hydroxyethyl acrylate were slowly added dropwise, during which a maximum
15 temperature of 70°C was attained. Thereafter the reaction mixture was held at
65°C until the NCO content was < 0.1%. Subsequently a mixture of 14.41 g of
2-hydroxyethyl acrylate and 2.14 g of zinc(II) ethylhexanoate was added dropwise.
The reaction mixture was heated up again and held at 80°C until after 3.5 h only a
very weak signal for uretdione groups was detected in the IR spectrum at
20 $\nu = 1768 \text{ cm}^{-1}$. 0.50 g of isophthalic dichloride was added and the mixture was
cooled rapidly to RT. The hydroxyethyl acrylate content of a sample taken was
found by gas chromatography to be 4.96%. 41.33 g of Desmodur N3400 and
0.07 g of Desmorapid® Z were then added. The mixture was stirred at 60°C until
in the IR spectrum at $\nu = 2272 \text{ cm}^{-1}$ there was no longer any signal present for
25 isocyanate groups. The hydroxyethyl acrylate content of a sample taken was found
by gas chromatography to be 0.14%. A product was obtained with a viscosity of
62,800 mPas/23°C, an APHA color number of 8 and an NCO content of less than
0.1%.

BMS 04 1 028-US

- 26 -

Example 2 - Inventive allophanate-containing binder

Example 1 was repeated with the difference that, instead of zinc(II) ethylhexanoate, 1.59 g of zinc(II) acetylacetonate were used. The reaction time following addition of the catalyst was 1.5 h. The hydroxyethyl acrylate content of a sample taken was found by gas chromatography to be 4.08%. 34.00 g of Desmodur N3400 and 0.07 g of Desmorapid® Z were then added. The mixture was stirred at 60°C until in the IR spectrum at $\nu = 2272 \text{ cm}^{-1}$ there was no longer any signal present for isocyanate groups. The hydroxyethyl acrylate content of a sample taken was found by gas chromatography to be 0.40%. 3.5 g of Desmodur N3400 were then also added. The mixture was stirred at 60°C until in the IR spectrum at $\nu = 2272 \text{ cm}^{-1}$ there was no longer any signal present for the isocyanate group. The hydroxyethyl acrylate content of a sample taken was found by gas chromatography to be 0.09%. A product was obtained with a viscosity of 71,000 mPas/23°C, an APHA color number of 91 and an NCO content of less than 0.1%.

Comparison Example 3 - Attempt to prepare an allophanate-containing binder

The catalysts described in US-A 2003/0153713 for the crosslinking of powder coating compositions containing uretdione group-containing curing agents and polymeric hydroxyl compounds without activated double bonds were examined for suitability:

Example 1 was repeated with the difference that, instead of the catalyst from Example 3, 0.51 g of tetrabutylammonium hydroxide was used as catalyst. The reaction mixture was heated to and held at 80°C until after 2 h only a very weak signal for uretdione groups was detected in the IR spectrum at $\nu = 1768 \text{ cm}^{-1}$. 0.10 g of benzoyl chloride was added and the mixture was cooled rapidly to RT.

BMS 04 1 028-US

- 27 -

During this cooling the reaction mixture turned cloudy. The hydroxyethyl acrylate content of a sample taken was found by gas chromatography to be 2.4%. 5.20 g of Desmodur[®] N3400 were added to the reaction mixture, which was stirred at 70°C until in the IR spectrum at $\nu = 2272 \text{ cm}^{-1}$ there was no longer any signal for isocyanate groups. The hydroxyethyl acrylate content of a sample taken was found by gas chromatography to be 0.17%. A cloudy product was obtained with a viscosity of 84,000 mPas/23°C and an NCO content of 0%.

Comparative Example 4 Attempt to prepare an allophanate-containing binder

- 10 The catalysts described in US-A 2003/0153713 for the crosslinking of powder coating compositions containing uretdione group-containing curing agents and polymeric hydroxyl compounds without activated double bonds were examined for suitability:
- 15 Example 1 was repeated with the difference that, instead of the catalyst from Example 3, 0.67 g of tetrabutylammonium fluoride was used as catalyst. The reaction mixture was heated to and held at 80°C until after 3 h only a very weak signal for uretdione groups was detected in the IR spectrum at $\nu = 1768 \text{ cm}^{-1}$. 0.10 g of benzoyl chloride was added and the mixture was cooled rapidly to RT.
- 20 During this cooling the reaction mixture turned cloudy, and a colorless precipitate formed. The hydroxyethyl acrylate content of a sample taken was found by gas chromatography to be 1.7%. 4.30 g of Desmodur[®] N3400 were added to the reaction mixture, which was stirred at 70°C until in the IR spectrum at $\nu = 2272 \text{ cm}^{-1}$ there was no longer any signal for isocyanate groups. The hydroxyethyl
- 25 acrylate content of a sample taken was found by gas chromatography to be 0.15%. A cloudy product was obtained with a viscosity of 92,000 mPas/23°C and an NCO content of 0%.

BMS 04 1 028-US

- 28 -

Comparison Examples 3 and 4 show that the catalysts which are suitable for crosslinking powder coating compositions containing uretdione group-containing curing agents and polymeric hydroxyl compounds are not suitable for the targeted synthesis of allophanates from uretdiones and alcohols. The resulting products are
5 cloudy and have a relatively high viscosity making them unsuitable for producing coatings.

Example 5 - Coating formulation and coating material

In each case a portion of the products from Examples 1 and 2 was mixed
10 thoroughly with 3.0% of the photoinitiator Darocur[®] 1173. Using a bone doctor blade with a gap of 90 µm the mixture was drawn down in the form of a thin film onto a glass plate. UV irradiation (medium pressure mercury lamp, IST Metz GmbH, Nürtingen, DE, 750 mJ/cm²) gave a hard, transparent coating which was solvent-resistant, had a pendulum hardness of 153 s or 154 s, could hardly be
15 damaged by scratching using steel wool (grade 0/0/0) in ten back-and-forth strokes with a force of 500 g directed onto the film and was not visibly altered after 100 back-and-forth strokes with a wad of cotton wool soaked in butyl acetate.

Although the invention has been described in detail in the foregoing for the purpose
20 of illustration, it is to be understood that such detail is solely for that purpose and that variations can be made therein by those skilled in the art without departing from the spirit and scope of the invention except as it may be limited by the claims.

BMS 04 1 028-US

- 29 -

Claims:

1. A process for preparing a radiation-curing binder containing allophanate groups which comprises reacting at temperatures of $\leq 130^{\circ}\text{C}$
 - 5 A) one or more compounds containing uretdione groups with
 - B) one or more OH-functional compounds which contain groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation,
 - C) optionally NCO-reactive compounds other than B),
 - 10 in the presence of
 - D) a catalyst comprising at least one zinc compound, to form allophanate groups by opening the uretdione ring.
2. The process of Claim 1 wherein said compounds containing
15 uretdione groups are prepared from hexamethylene diisocyanate.
3. The process of Claim 1 wherein component B) comprises 2-hydroxyethyl acrylate and/or 4-hydroxybutyl acrylate.
- 20 4. The process of Claim 2 wherein component B) comprises 2-hydroxyethyl acrylate and/or 4-hydroxybutyl acrylate.
5. The process of Claim 1 wherein component D) consists essentially of zinc compounds.
25
6. The process of Claim 1 wherein component D) comprises zinc acetylacetonate and/or zinc ethylhexanoate.
7. The process of Claim 2 wherein component D) comprises zinc
30 acetylacetonate and/or zinc ethylhexanoate.

BMS 04 1 028-US

- 30 -

8. The process of Claim 3 wherein component D) comprises zinc acetylacetonate and/or zinc ethylhexanoate.

9. The process of Claim 4 wherein component D) comprises zinc
5 acetylacetonate and/or zinc ethylhexanoate.

10. The process of Claim 1 wherein the reaction is carried out at a temperature of 40 to 100°C.

10 11. A radiation-curing binder containing allophanate groups which is prepared by a process comprising reacting at temperatures of $\leq 130^{\circ}\text{C}$
A) one or more compounds containing uretdione groups with
B) one or more OH-functional compounds which contain groups which react,
with polymerization, with ethylenically unsaturated compounds on
15 exposure to actinic radiation,
C) optionally NCO-reactive compounds other than B),
in the presence of
D) a catalyst comprising at least one zinc compound,
to form allophanate groups by opening the uretdione ring.

20

12. The radiation-curing binder of Claim 11 wherein said compounds containing uretdione groups are prepared from hexamethylene diisocyanate.

13. The radiation-curing binder of Claim 11 wherein component B)
25 comprises 2-hydroxyethyl acrylate and/or 4-hydroxybutyl acrylate.

14. The radiation-curing binder of Claim 12 wherein component B) comprises 2-hydroxyethyl acrylate and/or 4-hydroxybutyl acrylate.

BMS 04 1 028-US

- 31 -

15. The radiation-curing binder of Claim 11 wherein component D) comprises zinc acetylacetonate and/or zinc ethylhexanoate.

16. The radiation-curing binder of Claim 12 wherein component D)
5 comprises zinc acetylacetonate and/or zinc ethylhexanoate.

17. The radiation-curing binder of Claim 13 wherein component D) comprises zinc acetylacetonate and/or zinc ethylhexanoate.

10 18. The radiation-curing binder of Claim 14 wherein component D) comprises zinc acetylacetonate and/or zinc ethylhexanoate.

19. A coating composition comprising
- a) one or more of the radiation-curing binders containing allophanate groups
15 of Claim 11,
 - b) optionally one or more polyisocyanates containing free or blocked isocyanate groups, which are free from groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation,
 - 20 c) optionally compounds other than a), which contain groups which react, with polymerization, with ethylenically unsaturated compounds on exposure to actinic radiation, and optionally contain free or blocked NCO groups,
 - d) optionally one or more isocyanate-reactive compounds,
 - 25 e) one or more initiators, and
 - f) optionally solvents.

20. A substrate coated with a coating obtained from the radiation-curing binder containing allophanate groups of Claim 11.